

# CONTEX 1000



for safety shoes

conductive non woven

Laminated on fabrics, it makes the electrostatic charge dissipation uniform on the entire surface

**ESD**  
**conductive**



90 % Polyester  
5 % Conductive Filler  
5 % Synthetic Resin

TEST	UNITS	STANDARD	TYPICAL VALUES
weight	gr/m <sup>2</sup>		100
roll width	cm		150
thickness	mm	EN ISO 2589	0,40
electrical resistance	Ohm	EN ISO 20344	<1x10 <sup>5</sup>
relative humidity	%	EN ISO 20344	12

*The mentioned data are average values resulted on standard products of ours. The results are obtained either by own Laboratory or by Official Laboratories and they follow both internal and international Standard Norms. They are typical and strictly confidential data*