

FILCOHM 615

Conductive film developed for ESD shoes



Laminated on fabrics, it makes the electrostatic charge dissipation uniform on the entire surface.
When used in fussbett injected insoles, it has polyurethane barrier function.

*ESD
conductive*



*75 % Polyurethane
25 % Conductive Filler*

TEST	UNITS	STANDARD	TYPICAL VALUES
film weight	gr/m ²		35
film+carrier weight	gr/m ²		70
roll width	cm		155
thickness	mm	EN ISO 2589	0,03
electrical resistance	Ohm	EN ISO 20344	<1x10 ⁵
relative humidity	%	EN ISO 20344	12

The mentioned data are average values resulted on standard products of ours. The results are obtained either by own Laboratory or by Official Laboratories and they follow both internal and international Standard Norms. They are typical and strictly confidential data