

FUS 1011



for safety shoes fusbett insoles

Jersey fabric, made by Polyester with steel yarn.
The layer on the back side avoid polyurethane penetration through the fabric,
during the injection phase.
Conductive at 12% of Relative Humidity, according to the ESD standard CEI EN
61340-5-1:2016

conductive 12% RH

**polyurethane
injection barrier**



87 % Polyester
12 % Poliurethane
1 % Steel

TEST	UNTS	STANDARD	TYPICAL VALUES
weight	gr/m ²	UNI EN ISO 2286-2	220
thickness	mm	UNI ISO 2589	1,10
roll width	cm		150
electrical resistance	ohm	EN ISO 20344	<1x10 ⁵
relative humidity	%		12

The mentioned data are average values resulted on standard products of ours. The results are obtained either by own Laboratory or by Official Laboratories and they follow both internal and international Standard Norms. They are typical and strictly confidential data